

ABSTRACT

In a process of fabricating a narrow channel width PMOSFET device, the improvement of affecting reduction of negative bias temperature instability by use of F_2 side wall implantation, comprising:

a) forming a shallow trench isolation (STI) region in a substrate;

b) forming a gate on a gate oxide in the substrate;

c) forming a liner layer in said shallow trench isolation region and subjecting the liner layer to oxidation to form a STI liner oxidation layer;

d) implanting F_2 into side walls of said STI liner oxidation layer at a large tilted angle in sufficient amounts to affect reduction of negative bias temperature instability after a high density plasma fill of the STI F_2 implanted liner oxidation layer; and

e) filling the STI F_2 implanted structure from step c) with a high density plasma (HDP) fill to affect reduction of negative bias temperature instability.